

CLiQFLOW® 661 VR

Rheological Additive


CLiQFLOW 661 VR is a VOC compliant tin-free polyurethane thickener for aqueous clear and pigmented systems. The associative thickener increases both low and high shear viscosity and provides a shear-thinning flow behaviour to aqueous systems.

CLiQFLOW 661 VR improves anti-settling behaviour, sag resistance, and brush drag of aqueous systems; it will also improve the levelling properties, resulting in better gloss and a more uniform paint film after application.

CLiQFLOW 661 VR associates with both pigments and binders in an aqueous environment. The association with pigments and extenders makes the product particularly suitable for pigment concentrates and less dependent on other coatings ingredients.

Typical values:

Appearance:	white opaque liquid
Active Content:	ca. 40 %
Brookfield Viscosity:	< 20000 mPas
Density:	ca. 1.09 g/cm ³



Level of Use / Incorporation:

CLiQFLOW 661 VR can be added to the aqueous system at any production stage. In sensitive formulation, it may be recommended to add the product into the mill-base.

The optimum loading level should be determined for each system using a loading ladder study. In pigment concentrates, a level between 0.2 – 1.0% and for paint formulation, a loading between 0.2-2.0% is recommended.

CLiQFLOW 661 VR shows excellent compatibility with all kinds of aqueous binders.

CLiQFLOW 661 VR performance is not impacted by freezing, however, it is recommended to store in a cool dry place above 5°C. The minimum shelf life is 24 months when stored in unopened packages.

For information on health and safety information, please consult the Material Safety Data Sheet.

CLiQ SwissTech AG
Bahnhofstrasse 3
7320 Sargans
Switzerland

CLiQ SwissTech (Deutschland) GmbH
Bertram-Blank-Strasse 8A
51427 Bergisch Gladbach
Germany

CLiQ SwissTech (Netherlands) B.V.
Blauwborgje 31
9747AC Groningen
The Netherlands

sample@cliqswiss.com • info@cliqswiss.com

www.cliqswiss.com

This information is based to best of our knowledge and on test results obtained in our laboratory. It is given in good faith and should only regard as recommendations. No warranty is given, and it is advised to all users to evaluate the products carefully for their intended use. Please consider also all further information, labels, and especially the safety data sheet! For further questions, technical service and samples, please feel free to contact us.