

CLiQFLOW 615 is a rheological additive for aqueous systems based on a synthetic magnesium silicate. The layered silicate hydrates and delaminates in water creating a colourless and transparent colloidal dispersion.

CLiQFLOW 615 develops a thixotropic structure that provides anti-settling behaviour to pigments and fillers during storage, sag resistance and improved workability. The rheological additive has very little impact on gloss and does not negatively influence transparency and colour of the final system.

Typical values:

Appearance:	white creamy powder
Solids content:	ca. 90 %
Specific gravity:	ca. 2.5

Level of Use / Incorporation :

CLiQFLOW 615 is typically used at a loading level between 0.1 – 3% depending on the nature of the system. For storage stability a loading between 0.1 – 0.5% might be sufficient.

CLiQFLOW 615 requires some shear and dwell time for activation. Best efficiency is achieved when preparing a pre-gel (3-5% loading) and allowing sufficient swelling during agitation in water for 15 minutes. The pre-gel should be stored over night to allow full viscosity development.

A fully developed **CLiQFLOW 615** pre-gel can be added at any formulation step with simple agitation.

CLiQFLOW 615 should be stored in a cool dry place.

For information on health and safety information please consult the Material Safety Data Sheet.

CLiQ SwissTech AG
Bahnhofstrasse 3
7320 Sargans
Switzerland

CLiQ SwissTech (Deutschland) GmbH
Hauptstrasse 97
51465 Bergisch Gladbach
Germany

CLiQ SwissTech (Netherlands) B.V.
Zernikepark 6-8
9747AN Groningen
The Netherlands

sample@cliqswiss.com • info@cliqswiss.com

www.cliqswiss.com

This information is based to best of our knowledge and on test results obtained in our laboratory. It is given in good faith and should only regard as recommendations. No warranty is given and it is advised to all users to evaluate the products carefully for their intended use. Please consider also all further information, labels, and especially the safety data sheet! For further questions, technical service and samples, please feel free to contact us.

Version: 20160209