

CLiQSPERSE® 162

Wetting Agent

CLiQSPERSE 162 is a highly efficient anionic wetting agent for both aqueous and non-aqueous systems. It is applied in coatings and pigment concentrates to improve pigment/substrate wetting or colorant compatibility.

CLiQSPERSE 162 is used as wetting agent in aqueous and universal pigment concentrates in combination with an appropriate dispersing agent. The strongly anionic product improves storage stability, colour development, and colour acceptance of pigment concentrates.

CLiQSPERSE 162 used in aqueous or non-aqueous base paints strongly improves compatibility of pigment concentrates with a variety of coatings systems; especially when mixing hydrophilic universal pigment concentrates with non-aqueous long oil alkyd base paints of a hydrophobic nature.

Typical values:

Appearance:	Clear yellowish liquid
Solids content:	ca. 60%
pH (1% solution):	5 - 6.5
Density (20°C):	1.09 g/cm ³

Level of Use / Incorporation:

CLiQSPERSE 162 is best dispersed with pigments and extenders for maximum efficiency. Depending on the pigment nature, a loading level between 0.5 and 5% is recommended for pigment concentrates. For paint formulations, a loading level between 0.1-0.6 % is recommended.

CLiQSPERSE 162 is compatible with most aqueous general industrial and architectural systems based on a variety of binder systems.

CLiQSPERSE 162 should be stored in a cool dry place. The minimum shelf life is 36 months when stored in unopened packages.

For information on health and safety information, please consult the Material Safety Data Sheet.

CLiQ SwissTech AG
Bahnhofstrasse 3
7320 Sargans
Switzerland

CLiQ SwissTech (Deutschland) GmbH
Bertram-Blank-Strasse 8A
51427 Bergisch Gladbach
Germany

CLiQ SwissTech (Netherlands) B.V.
Blauwborgje 31
9747AC Groningen
The Netherlands

sample@cliqswiss.com · info@cliqswiss.com

www.cliqswiss.com

This information is based to best of our knowledge and on test results obtained in our laboratory. It is given in good faith and should only regard as recommendations. No warranty is given and it is advised to all users to evaluate the products carefully for their intended use. Please also consider all further information, labels, and especially the safety data sheet! For further questions, technical service, and samples, please feel free to contact us.

Version: 5-Feb-24